

SGG COOL-LITE®
SKN 144 II

*High performance
solar control glass
with advanced
thermal insulation
properties*



SGG COOL-LITE® SKN 144 II

*Combining high performance with excellent neutrality,
for optimal solar control and thermal efficiency*

Applications

SGG COOL-LITE SKN 144 II is a 'to be tempered' solar control coating for use in residential or commercial buildings alike, either for façades or overhead glazing. Due to the unique properties of the coating, it is ideally suited to applications requiring toughened or heat-strengthened glass.

Description

SGG COOL-LITE SKN 144 II is a solar control product with a high performance coating. The coating is applied to SGG PLANILUX clear float glass by cathodic sputtering under vacuum conditions.

SGG COOL-LITE SKN 144 II forms part of the ever-evolving range of 'to be toughened' neutral solar control coatings from SAINT-GOBAIN GLASS.

In order to achieve its superior thermal properties, solar control properties and neutral appearance, SGG COOL-LITE SKN 144 II must always be toughened or heat-strengthened before assembly into a double-glazed unit. For optimum performance and aesthetics the SGG COOL-LITE SKN 144 II coating should always be positioned on face 2 of a double-glazed unit.

Benefits

SGG COOL-LITE SKN 144 II is designed to offer exceptional solar and thermal performance:

- very low g-value of 0.23
- optimum U-value of 1.1W/m²K
- neutral appearance both in transmission and exterior reflection
- good levels of natural light transmission

SGG COOL-LITE SKN 144 II can be used to improve the energy efficiency of buildings by considerably reducing overheating and the need for costly air conditioning. It is particularly suited to large areas of glazing where superior solar control performance is required whilst at the same time noticeably reducing excessive heat loss.

Range

SGG COOL-LITE SKN 144 II is available in 6000mm x 3210mm dimensions, in 6, 8 and 10mm thicknesses (12mm available on request) allowing for over-sized high-specification units.

Instructions for use

SGG COOL-LITE SKN 144 II must be toughened from stock due to the absorption of the coating requiring toughened glass for thermal safety reasons.

Technical Specifications

Performance Data

	DGU with SGG COOL-LITE SKN
Internal Pane	SGG PLANILUX
External Pane	SGG COOL-LITE SKN 144 II
Composition in mm	6(16)6
Coating Positions	Face 2
LT	40%
LRe	20%
g-value*	0.23
Shading Coefficient	0.27
U-Value in W/m ² K	
Air	1.4
90% Argon	1.1

SGG COOL-LITE SKN 144 II meets the durability requirements of class C of European standards EN 1096-1 and -2.
*Light and solar performance according to EN 410

SGG COOL-LITE, SGG PLANILUX and all other devices and logos are registered trademarks of Saint-Gobain.



Saint-Gobain Glass UK Ltd
Weeland Road, Eggborough
East Riding of Yorkshire, DN14 0FD, UK
www.saint-gobain-glass.com

Distributor